


High Tack Pressure Sensitive Adhesive Tapes

HIGH TACK PRESSURE SENSITIVE ADHESIVE TAPES



Eccosorb SS-tapes are very high tack PSA tapes specifically designed for use with Laird’s absorbers.

There are several PSA’s offered: Eccosorb® SS6M for silicone absorbers
 Eccosorb® SSV for vinyl materials
 Eccosorb® SS10 for Eccostock® PP

Eccosorb SS-tapes are cleanly cut with steel roll dies or via water-jet cutting.

FEATURES AND BENEFITS

- High tack
- Factory installed

MARKETS

- Commercial Telecom
- Security and Defense

SPECIFICATIONS

TYPICAL PROPERTIES	SS6M	SS10	SSV
Adhesive Type	Acrylic	Acrylic	Acrylic
Adhesive Carrier	0.5 mil Polyester	0.5 mil Polyester	0.5 mil Polyester
Tape Thickness	4.5 mils	4.6 mils	3.1 mils
Peel Adhesion to steel, lb./in. width	4.7	7.5	4.7
Tensile Strength, lb./in.	10	12	10
Elongation	60%	80%	60%
Typical Service Temperature °C(°F)	-40 to 121 (-40 to 250)	10 to 121 (50 to 250)	-40 to 121 (-40 to 250)

APPLICATIONS

- Eccosorb SS-tapes are used throughout many applications where high bond reliability and UV resistance is required.
- The tapes are ideally suited for applications such as commercial microwave devices where the speed and convenience of a peel and stick adhesive is desired.
- They have shown effective in applications involving shock and vibration, temperature cycling and high humidity.
- Adhesion testing with SS6M was also performed with material attached to a housing at 93 °C for 24 hours, mounted at 90°, and heated to 149 °C for 24 hours. No slouching was seen and bond strength is excellent.
- In general longer residence time yields higher peel values.

USA: +1.866.928.8181
 Europe: +49.8031.24600
 Asia: +86.755.2714.1166
www.laird.com



AVAILABILITY

- Eccosorb SS-tapes are factory installed, which utilize a proprietary process resulting in a superior adhesive bond. When applied in this manner, bond strength is far superior when compared to those adhesives applied to the material after its manufacture.
- Additional Specific/Customized PSA are available like automotive high temperature grade



Eccosorb[®]SS-Tapes

High Tack Pressure Sensitive Adhesive Tapes

INSTRUCTIONS FOR USE

- Simply peel the release paper off of the adhesive backing and apply.
- The use of heat and pressure will help to increase the initial bond of the material to the substrate. Surfaces to be bonded should be cleaned, dry, and free from grease and oil.
- Eccosorb SS6M should not be bonded to any material that may contain migrating plasticizers, rather SSV should be used in that case.

USA: +1.866.928.8181

Europe: +49.8031.24600

Asia: +86.755.2714.1166

www.laird.com



RFP-DS-SS Tapes 011616

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2015 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights.