



### SNC45RXP

A lower deflection force, nickel/graphite filled moisture curable silicone Form-In-Place grade. Thanks to its unique filler technology, SNC45RXP shows the lowest shore hardness in Laird's cure FIP resulting in minimum required compression force when mounting assemblies. It shows very good shielding performance along with good compression set ending in overall long-term reliability.

Laird's Form-In-Place is an automated system for dispensing conductive elastomer EMI shielding and grounding gaskets onto metal or plastic substrates. All Laird Paste can be dispensed to triangular profile directly.

### TYPICAL VALUES

	TEST METHOD	UNITS	SNC45RXP
<b>Elastomer</b>			Silicone
<b>Filler Type</b>			Nickel/Graphite
<b>ELECTRICAL PROPERTIES</b>			
<b>Volume Resistivity</b>	WI-QA-4153	ohm-cm	0.04
<b>Shielding Effectiveness, 200 MHz to 10 GHz</b>	MIL-DTL-83528C, Para. 4.5.12	dB	>80
<b>PHYSICAL PROPERTIES</b>			
<b>Hardness</b>	ASTM D2240	Shore A	45
<b>Density (uncured)</b>	ASTM D792	g/cm <sup>3</sup>	1.60
<b>(cured)</b>		g/cm <sup>3</sup>	1.80
<b>Compression Set</b>	ASTM D395	%	15
	125°C, 22hrs		
<b>Adhesion Strength</b>	to Aluminum surface COM-SZ-QA-WI-0203	N/cm <sup>2</sup>	>150
<b>Compression-Deflection <sup>(a)</sup></b>	LT-FIP-CLE-07		
<b>at 20% compression</b>		lb/in	0.60
<b>at 40% compression</b>		lb/in	1.60
<b>Temperature Range</b>		°C	-55 to 125
<b>UL Flammability Rating</b>	UL94 (between AI)		V0

USA: +1.866.928.8181

Europe: +49.8031.24600

Asia: +86.755.2714.1166

[www.laird.com](http://www.laird.com)



EMI-DS-SNC45RXP\_03312021

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2021 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third-party intellectual property rights.



# SNC45RXP

## Form-In-Place

### CURING REQUIREMENTS

<b>Curing Conditions</b>	15 to 40°C, 50%RH
<b>Full Cure<sup>(b)</sup></b>	24 hours

(a) Compression-deflection bead size 0.62mm (H) × 0.70mm (W)

(b) Time to effectively cure a bead will necessarily depend on individual conditions, including but not limited to bead size, shield size and weight, oven capacity, and oven ramp-rates.