

PRODUCT DESCRIPTION

Tgard™ 210B is a high-performance interface pad, consisting of a silicone/boron nitride composite. These fiberglass-reinforced pads are used when the lowest thermal resistance and high consistent dielectric strength are required.

A high-tear, cut-through and puncture-resistant product, the Tgard™ 210B is tough and strong. Burrs cause no problems for the material and the pad will not dry out, crack, or fail when pressured between mating parts.

FEATURES & BENEFITS

- High thermal conductivity of 5.0 W/m·K
- High dielectric breakdown voltage 6,000 volts
- Resistant to tears and punctures
- UL94 V0 rated

APPLICATIONS

- Automotive control units
- Power conversion equipment
- Power semiconductors (To packages, MOSFETs and IGBTs)
- Automotive control units
- Power Supplier



PROPERTY	TEST METHOD	Tgard™ 208B	Tgard™ 210B	Tgard™ 212B
Supporting material		Fiberglass	Fiberglass	Fiberglass
Color	Visual	White	White	White
DBV ^{*1} 50mm probe	ASTM D149	5000	6000	7000
Volume resistivity (ohm-cm)	ASTM D257	1.2x10 ¹⁵	1.2x10 ¹⁵	1.2x10 ¹⁵
Dielectric constant @1MHz	ASTM D3380	3.03	3.03	3.03
Thickness mil (mm)		8 (0. 2)	10 (0. 25)	12 (0. 3)
Thermal resistance (@100PSI) °C-in ² /W	ASTM D5470	0. 20	0. 25	0.27
Thermal conductivity	ASTM D5470 (modified)	5.0W/mk	5.0W/mk	5.0W/mk
Hardness (Shore A)	ASTM D2240	80	80	80
Operation Temperature range		-60°C to 200°C	-60°C to 200°C	-60°C to 200°C
UL Flammability rating	UL	94V0	94V0	94V0

*1 point- test imperial value

USA: +1.866.928.8181
Europe: +49.8031.24600
Asia: +86.755.2714.1166

www.laird.com



Standard options:

Request no adhesive with "A0" suffix. Request adhesive on one side with "A1" suffix. Double-sided adhesive is not available. Adhesive is intended to be a mounting aid and not for permanent bonding. Thermal resistance increase may be seen in comparison to material with no adhesive.

Product Part Number System

Example 1: Tgard™208B A0 = 0.008"(0.20mm) thick Tgard™ 200B product
Example 2: Tgard™212B A1= 0.012" (0.3mm) thick Tgard™ 200B product with one side adhesive

Configurations Available:

Sheets and die-cut parts are available with and without adhesive. Die cut parts on a roll are available with adhesive only. Contact your sales representative if any special shape is required.

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

THR-DS-Tgard-200B 03132023

Any information furnished by Laird Technologies, Inc. or any of its affiliates or agents ("Laird") is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird materials rests with the end user. Laird makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird materials or products for any specific or general uses. Laird shall not be liable for incidental or consequential damages of any kind. All Laird products are sold pursuant to the Laird's Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2022 Laird Technologies, Inc. All Rights Reserved. Laird™, Laird Technologies™, the Laird Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. DuPont™ is a trademark or registered trademark of DuPont de Nemours, Inc., or an affiliate company thereof. Other marks may be owned by third parties. Nothing herein provides a license under any Laird or any third-party intellectual property rights.